

## Technical Data Sheet

Product code: MCN 3000CF  
Composition: 30% Bronze + 10% Carbon Fiber +60%virgin PTFE

Property	Measuring method	Units	NFF	FF
<b>Bulk density</b>	ASTM D-4849	g/L	--	1010
<b>Average particle size,D50</b>	ASTM D-4894	μm	--	660
<b>Flow Index</b>	INTERNAL	Sec/50g	--	2.1
<b>Specific gravity</b>	ASTM D-4894	g/cm	--	3.01
<b>Hardness,Shore D</b>	ASTM-D2240		69	70
<b>Tensile Strength</b>	ASTM D-4894	M Pa	23	24
<b>Elongation at break</b>	ASTM D-4894	%	270	265
<b>Shrinkage</b>	INTERNAL	%	2.1	2.1
<b>Recommended molding pressure</b>		Kg/cm <sup>2</sup>	500	550
<b>Max. sintering temperature</b>		°C	--	380

**MANUFACTURER:** QINGDAO SHINHAN EP CO., LTD.  
QINGDAO / SHANDONG / CHINA.

( 1 ) Approved by :HYUNHEE, HONG	( 2 ) Revision No. 02	( 3 ) Edition Date : 08 / 2012
----------------------------------	-----------------------	--------------------------------