

## Technical Data Sheet

Product code: MCN 10EKONOL  
Composition: 10%EKONOL + 90% virgin PTFE

Property	Measuring method	Units	NFF	FF
<b>Bulk density</b>	ASTM D-4849	g/L	--	--
<b>Average particle size,D50</b>	ASTM D-4894	µm	--	--
<b>Flow Index</b>	INTERNAL	Sec/50g	--	--
<b>Specific gravity</b>	ASTM D-4894	g/cm	2.2	--
<b>Hardness,Shore D</b>	ASTM-D2240		63	--
<b>Tensile Strength</b>	ASTM D-4894	M Pa	23	--
<b>Elongation at break</b>	ASTM D-4894	%	320	--
<b>Shrinkage</b>	INTERNAL	%	2.1	--
<b>Recommended molding pressure</b>		Kg/cm <sup>2</sup>	500	--
<b>Max. sintering temperature</b>		°C	--	--

**MANUFACTURER:** QINGDAO SHINHAN EP CO., LTD.  
QINGDAO / SHANDONG / CHINA.

( 1 ) Approved by :HYUNHEE, HONG	( 2 ) Revision No. 02	( 3 ) Edition Date : 08 / 2012
----------------------------------	-----------------------	--------------------------------